

Product information | TECHNICAL DATA SHEET

STONE SHIELD

500 ml, 18.34 Oz, 520 g.

GENERAL DESCRIPTION

Stone Shield is a coating designed to effectively protect different parts of the vehicle against gravel that is projected during driving. Its thickness considerably muffles the sounds and vibrations of the engine, and can also be applied as a protector of the lower parts of the bodywork and/or wheel arches. It is designed to reproduce the manufacturer's original finish, with excellent adhesion, elasticity, and a strong cold and corrosion resistance. Once dry, it can be recoated with bodywork base coat paint.

FEATURES

- Ultra-fast drying.
- Excellent elasticity.
- Easy to apply and recoat.
- Protection against corrosion.
- High thickness.

APPLICATIONS

It serves as an anti-corrosion protective coating for vehicles, trucks, and buses.

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Shake the spray can well before use, approximately 2-3 minutes after hearing the noise of the mixing ball. It is also recommended to shake it well during the application of the product.
- Apply on clean, dry and rust-free surfaces. Sand the area, dry clean and remove grease. On already painted surfaces, sand and apply a primer on unpainted areas.
- Apply in two or three cross coats. The desired texture is obtained by varying the application distance. Do not apply on engines, gears, oil pans, exhaust pipes, braking systems, shock absorbers or other moving parts.
- The product can be recoated after 1-3 h, depending on drying conditions.
- After using the aerosol, turn the can upside down and press the nozzle for several seconds until only gas comes out to prevent clogging. If the nozzle clogs, replace it with a new one.
- Do not spray on connected equipment and use only in well-ventilated areas. Do not breathe in the fumes from the aerosol.
- Request safety datasheets.

PHYSICAL PROPERTIES

Binder:	Alkyd modified.
Color:	Black
Shine 60°:	<30%
Dry to the touch (ASTM D-1640 ISO 1517):	5'
Total drying (ASTM D-1640 ISO 1517):	1-3 h
Dry thickness:	30-35 µ/capa
Theoretical yield (continuous painting):	2 m ²
Product life: (Well Stored)	5 Years
Recoating:	15-30' between layers- 1-3 h Basecoat
Application conditions:	T° environment min. 8°C
	T° superficie de 5-50°C
	Humidity Max. 85% R.H.P

* Adherence tests were performed on steel.

290424

IMAGE



LABEL



Negro / Black
EX015PR0002

CAP SYSTEM



PACKAGING

Nominal capacity 500 ml.
Heat resistance of packaging: <50°C
Propellant: DME

Box (6 units)
255 X 140 X 200 mm.

